

1/18 RTS
"PROCESS FOR MANUFACTURING REINFORCED TILES OR PANELS OF
AGGLOMERATED MATERIAL WITH A METALLIC PLATE AS WELL AS
REINFORCED TILES OR PANELS OF AGGLOMERATED MATERIAL WITH
A METALLIC PLATE OBTAINED THROUGH SAID PROCESS"

5

TECHNICAL FIELD

The present invention concerns a procedure for the
10 production of sheets or tiles made from agglomerate
material, in particular a material generally consisting
of marble and/or quartz and/or sand and/or binding
resins and/or granite-based mixtures, also comprising
possible intrusions of various kinds, such as elements
15 in metal, glass, wood, etc., these sheets or tiles being
equipped with a metal reinforcement plate positioned on
the lower surface.

The invention also refers to sheets or tiles
manufactured according to this procedure.

20 The invention applies mainly to the industrial
processing field of marble, stone, granite and the like.

BACKGROUND ART

Sheets or tiles in agglomerate material presenting
an internal reinforcement structure are frequently used
25 for laying so-called raised or floating floors in which
the sheets or tiles are positioned on top of an
appropriate wire grid which is raised with respect to
the ground thus making it possible to obtain a hollow
space with a predetermined height, allowing the laying
30 of large quantities of electrical and/or hydraulic

*This paper or fee is being deposited with the
United States Postal Service "Express Mail
Post Office to Addressee" under 37 CFR §
1.10 Mailing Label No. EV 311277230US*

ducting and their easy maintenance or modification.

While on one hand raised or floating floors present considerable advantages, including those described above, on the other they involve a series of drawbacks
5 which limit their construction and use or make them difficult.

A first drawback presented by raised or floating floors made from composite material is due to the fact that these floors are usually electrically ground-
10 insulated.

This implies an unfavourable accumulation of electrostatic charges on objects which are present on or which move on this floor, an effect which is unacceptable for numerous precision electronic devices
15 but which may be even more simply disadvantageous if these electrostatic discharges involve the people who walk across the floor.

A further limitation usually involved in the construction of raised or floating floors consists of
20 the fact that the sheets must directly support the weight of considerable loads and must therefore be fairly thick in order to withstand maximum breaking loads in compliance with safety regulations.

All this inevitably means not only great structural
25 and working limitations but also high costs and lengthy and difficult laying times for these floors.

The Italian document VR94A000068 describes a procedure for the production of sheets made from agglomerate material comprising a series of processing
30 stages, specifically:

- an initial stage consisting of the crushing of the various materials making up the agglomerate;
- a second stage consisting of the mixing of the crushed materials in order to obtain a product which is as homogeneous as possible, during which the binding resins are added;
- a third stage consisting of the pressing and compacting of the agglomerate during which the required shape is obtained and in which a wire or fibre mesh is buried, this being formed by a plurality of wires arranged according to a predetermined layout and whose ends are situated at the same level as or protrude beyond the lower surface of the sheet;
- a fourth stage in which the sheet is hardened at a predetermined temperature;
- a fifth stage in which at least one side of the sheet is smoothed and polished;
- a sixth stage in which the sheet is cut to size, chamfered, gauged and flared, followed by unloading of the end products.

A procedure such as the one described above makes it possible to obtain sheets made from agglomerate material, with precisely predetermined lengths, widths and thicknesses, and which is performed in a continuous process on a specially designed plant.

In spite of the presence of the wire-mesh consisting of wires as described above, the previously mentioned disadvantages are still present, particularly as regards the electrostatic charge.

In fact, during the hardening stage the resin envelops the metal surface of the wires forming the reinforcement mesh, creating an insulation film which does not permit effective discharge of the accumulated
5 electrostatic charge.

Document US-A-4640854 discloses a composite plate for double floors comprising a pan-shaped wrapper for receiving therein a flowable and hardenable filler material. The wrapper comprises a plurality of
10 downwardly extending projecting blocks containing the filler material.

Documents US-A-4833845 and US-A-5057355 disclose a metallic shallow pan serving for the production of a self-supporting composite plate, wherein the pan forms
15 the outside wrapper for a filler with high compression resistance such as anhydrite.

DESCRIPTION OF THE INVENTION

The present invention aims to overcome the above-
20 mentioned drawbacks and disadvantages, and to therefore provide a procedure which allows the production of sheets or tiles made from agglomerate material designed to be advantageously used in laying floating floors.

This is achieved by implementing the features
25 described in the main claim.

The dependent claims describe particularly advantageous forms of embodiment of the procedure according to the invention.

Finally, claim 5 describes a sheet or tile made
30 from agglomerate material advantageously obtained by

means of the procedure according to the invention.

According to a fundamental feature of the invention, a metal plate is positioned inside the tile or sheet. The structure of this plate is the result of the processing of a laminar element, obtained for example by die forming, presenting an irregular structure for example with cavities and protuberances designed to accommodate the agglomerate mixture which, during the polymerisation and hardening stage, binds to the plate which is therefore either embedded in the sheet or tile or forms the base thereof.

As far as the other stages of the procedure are concerned, there are no technically significant variations with respect to what is already known and the end result is a tile or sheet reinforced with a metal plate which is embedded in its structure, or covers its lower surface to form a single object.

The use of this type of tile or sheet makes it possible to resolve the problems mentioned above, typical of background art.

When using the sheets or tiles to lay raised or floating floors, the metal reinforcement plates can be connected to each other, thus allowing a continuous and precise ground-discharge of the electrostatic charge generated on the surface of the floor or of the objects in contact with the floor, preventing the discharges from damaging the equipment or affecting the people walking across the floor.

In fact thanks to the particular structure of the metal plate and its extensive surface, although the

resin contained in the mixture forming the agglomerate binds to the plate during the polymerisation and hardening stage, also due to the presence of elements that make its surface irregular and allow an excellent
5 adherence of the mixture, it does not lead to the formation of an insulating film as in the solutions known to background art.

DESCRIPTION OF THE DRAWINGS

Other features and advantages of the invention will
10 become evident on reading the following description, given as a non-binding example, with the help of the enclosed drawings, in which:

- figure 1 a metal plate according to an embodiment of the present invention;
- 15 - figure 2 shows a perspective view from above, partially in cross-section, of a sheet or tile according to an embodiment of the present invention; and
- figure 3 shows a perspective view from below, of
20 the base of the sheet or tile according to figure 2.

DESCRIPTION OF A FORM OF EMBODIMENT

In the figures, the reference number 10 generally indicates a sheet or tile made from stone agglomerated
25 material, manufactured by means of the procedure according to this invention.

The materials normally used for the production of sheets or tiles 10 of this type comprise a variety of mixtures such as for example marble of different types
30 or colours bonded by resins, marble bonded with

predetermined percentages of quartz, sands bonded with binding resins and various other possibilities widely known to the background art.

5 The procedure for manufacturing the sheets or tiles
10 is typically carried out on an automated plant controlled by a computerised system in the various processing stages.

10 The first stage of the procedure foresees the crushing of the various components in order to achieve the required granulometry, particularly when marble, granite or quartz are used.

 In the second stage the crushed products are mixed together in a special mixing machine and an appropriate synthetic resin acting as a binder is added.

15 In the third stage the mixture is poured into a die of a press. The action of the press on the mixture, together with the activation of a vibrator device and a vacuum device, makes it possible to model a sheet or tile according to a predetermined shape, thickness and
20 density, and with a homogeneous structure free of gas or air bubbles.

 According to a form of embodiment of the present invention, a metal plate 11 is positioned on the bottom of the pressing die before the mixture to be pressed is
25 poured into the die.

 Once the pressing and hardening has been carried out, the metal plate 11 constitutes a single object with the sheet or tile 10, forming the lower surface.

30 The subsequent stages of the procedure are then carried out in the traditional way.

The sheet or tile 10 is first conveyed inside a kiln in which the polymerisation of the synthetic resin and the consequent hardening of the sheet or tile take place, with particular temperature conditions and
5 hardening times, well known to experts in the sector.

On leaving the kiln, the sheet or tile 10 is conveyed towards the next processing stations for the subsequent smoothing and polishing of the upper surface, the cutting to size according to the required shape,
10 the chamfering, gauging and flaring operations, and then to any waxing, drying and packaging stations.

The above description shows that the procedure according to this invention differs from what is already known to the background art by the insertion of a metal
15 plate during the product pressing stage.

This particular solution makes it possible to obtain an end product with completely new features with respect to what is already known.

In fact, the insertion of the plate makes it
20 possible to completely discharge any electrostatic charge accumulated on the sheet or tile by connecting it to ground electrically or by connecting the entire floor once the various sheets or tiles of which it consists are connected to each other as in the case of a raised
25 floor.

This particular ability to discharge the electrostatic current is made possible by the presence of the plate and its extensive contact surface with the conductor elements inside the agglomerate structure.

30 The metal plate 11 according to this invention can

be obtained for example from an element die-formed or rolled in such a way as to present a series of cavities or protuberances which allow excellent adherence of the resin to the plate.

5 In figure 1 these cavities are represented by elements 12 which expand from the bottom of the plate. According to other variations, not shown in the drawings, these cavities can also be knurled or rippled, or protuberances or elements protruding towards the
10 mixture forming the agglomerate.

According to a particular embodiment of the invention, the metal plate can be made from aluminium.

The other considerably important function of the metal plate 11 is to reinforce the sheet or tile 10
15 giving it a much higher breaking load compared with a sheet of the same size constructed according to known techniques.

This means that sheets or tiles 10 much thinner than traditional ones but with the same required
20 breaking load can be used to lay a floor.

For example, according to this invention it is possible to use sheets or tiles with a thickness of between 10 and 20 mm to construct raised or floating floors and with a breaking load which is the same as
25 that of traditional panels, sheets or tiles, which are normally at least 30-35 mm thick.

As already mentioned above, the possibility of using thinner sheets or tiles means less material, less weight, easier laying and, basically, a remarkable
30 saving in costs, despite the insertion of the metal

plate.

The invention is described above with reference to a preferred form of embodiment.

It is nevertheless clear that the invention is not
5 limited to this form of embodiment but is also
susceptible to numerous variations with the same aims,
within the framework of technical equivalents. For
example, the metal plate can easily be inserted in the
die after having poured a given quantity of material
10 inside the die. In this case the final product is a tile
or sheet where the metal plate is not forming the base
thereof, and it is rather embedded in the tile or sheet.
The same technical results as mentioned above, in what
concerns discharging electrostatic charges and raising
15 the breaking load of the tile or sheet, are achieved.